F12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 31 December 2003 (31.12.2003)

PCT

(10) International Publication Number WO 2004/000904 A1

(51) International Patent Classification⁷: 18/42, A61L 27/18

C08G 18/10,

(21) International Application Number: PCT/SE2003/001085

(22) International Filing Date:

23 June 2003 (23.06.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 0201948-7

20 June 2002 (20.06.2002)

(71) Applicant (for all designated States except US): ARTIM-PLANT AB [SE/SE]; Hulda Mellgrens gata 5, S-421 32 Västra Frölunda (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): GISSELFÄLT, Katrin [SE/SE]; Vidblicksgatan 5, S-412 57 Göteborg (SE).

(74) Agent: ALBIHNS GÖTEBORG AB; Box 142, S-401 22 Göteborg (SE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP. KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, TE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

of inventorship (Rule 4.17(iv)) for US only

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: LINEAR BLOCK POLYMER

(1)

(57) Abstract: Linear block polymer according to Formula (1) wherein R1 is derived from a diamine, e.g. ethylene diamine, 1,2diamino propane or 1,3-diamino propane; R2 is derived from an aromatic diisocyanate; R3 is derived from an esterdiol; R4 is derived from dibutyl amine or ethanolamine; Where 08, wherein the monomers from which R2 and R3 are derived from are added in such amounts that the molar ratio between R2 and R3 is larger than 2:1.

